

ENVIRONMENTAL PROFILE OF THE PEX PIPE SYSTEM FOR HOT AND COLD WATER (CRADLE-TO-GRAVE) IN ABSOLUTE FIGURES PER FUNCTIONAL UNIT

IMPACT CATEGORY	Abiotic depletion	Acidification	Eutrophication	Global warming	Ozone layer depletion	Photochemical oxidation
Life cycle phases	kg Sb eq	kg SO2 eq	kg PO4--- eq	kg CO2 eq	kg CFC-11 eq	kg C2H4 eq
PRODUCT STAGE						
Production raw materials for PEX	0,00580	0,00114	0,00010	0,33595	0,000000004	0,00011
Transport of raw materials for PEX pipe to converter	0,00006	0,00003	0,00001	0,00825	0,000000001	0,000001
Extrusion PEX pipes	0,00144	0,00086	0,00056	0,19284	0,000000001	0,00004
Production of PPSU fittings	0,00103	0,00041	0,00040	0,10527	0,000000005	0,00012
Production of brass fittings	0,00030	0,00148	0,00160	0,04336	0,000000003	0,00006
CONSTRUCTION PROCESS STAGE						
Transport of complete PEX pipe system to the building site (apartment)	0,00067	0,00035	0,00010	0,09614	0,000000001	0,00002
Installation of PEX pipe system (in apartment)	0,00066	0,00031	0,00018	0,09915	0,000000004	0,00004
USE STAGE						
Operational use of PEX pipe system	0	0	0	0	0	0
Maintenance of PEX pipe system	0	0	0	0	0	0
END OF LIFE STAGE						
Transport of PEX pipe system to EoL (after 50 years of service life time apartment)	0,00004	0,00002	0,00001	0,00603	0,000000001	0,000001
EoL of PEX pipe system (after 50 years of service life time of apartment)	-0,00025	-0,00011	-0,000094	0,05003	-0,000000001	-0,00001
Total	0,00976	0,00451	0,00286	0,93702	0,0000008	0,00037
<p>A: contribution > 50 %: most important, significant influence</p> <p>B: 25 % < contribution ≤ 50 %: very important, relevant influence</p>						

More detailed information about this material comparison can be obtained via www.teppfa.eu or by contacting TEPPFA at: info@teppfa.eu



The European Plastic Pipes and Fittings Association (TEPPFA) is the trade association representing manufacturers and national associations of plastic pipe systems in Europe. We are actively involved in the promotion of plastic pipe systems for all applications. We want to raise awareness of the value that plastic pipe systems offer for a sustainable future.


Registered office:
Avenue de Cortenbergh, 71
1000 Brussels
Belgium

tel: +32 2 736 24 06
fax: +32 2 736 58 82
e-mail: info@teppfa.eu

www.teppfa.eu

Cross-linked polyethylene (PEX) pipe systems vs copper environmental impact comparison

An independent study following ISO 14040 and 14044 methodology by the respected Flemish Institute for Technological Research (VITO), and validated by the Denkstatt sustainable development institute in Austria, is conclusive in its findings that plastic pipe systems made from cross-linked polyethylene (PEX) for plumbing hot and cold solid wall applications have a lower environmental impact than those made from copper.



RELATIVE SIZE OF ENVIRONMENTAL FOOTPRINT

COPPER



PEX



To make a fair comparison between these two different materials and determine the environmental impacts of both, each stage of their lifecycle was analysed.

"Environmental footprints" can be either adverse or beneficial. Adverse effects such as emitting greenhouse gases may arise in either the product's production or disposal process; beneficial effects help to reduce greenhouse gas emissions by saving energy whilst the product is in use.

DETERMINING A PRODUCT'S ENVIRONMENTAL FOOTPRINT

A scientifically-based full Life Cycle Assessment (LCA) is the standardised method for fairly comparing the environmental impacts of different products or services. This type of assessment involves systematically collecting and evaluating quantitative data on the inputs and outputs of material, energy and waste flows associated with a product over its entire life cycle. Therefore a whole range of processes need to be assessed to calculate overall impacts, beginning with the manufacturing of raw materials, to transforming them into products; continuing through the product's transportation and installation, the product's lifetime of use, and ultimately, the product's disposal or re-processing at the end of life.

The findings of LCA assessments are typically published in the form of Environmental Product Declarations (EPDs) to help communicate a product's overall environmental impact.

The VITO study involved collecting data on plastic pipe systems from companies covering more than 50% of the European market. Data for copper was based on publicly available information.

ENVIRONMENTAL IMPACT CRITERIA

The environmental impact of each pipe material was assessed against six different criteria across its full life cycle.



'Abiotic-depletion' potential: the over-extraction of minerals, fossil fuels and other non-living, non-renewable materials which can lead to exhaustion of natural resources.



'Acidification' potential: emissions, such as sulphur dioxide and nitrogen oxides, from manufacturing processes, result in acid rain which harms soil, water supplies, human and animal organisms, and the ecosystem.



'Eutrophication' potential: which arises from of the over-fertilisation of water and soil by nutrients (such as nitrogen and phosphorous). This speeds up plant growth and kills off animal life in lakes and waterways.



'Global warming' potential (its carbon footprint): the insulating effect of greenhouse gases - CO₂ and methane - in the atmosphere is a major contributor to global warming, affecting both human health and that of the ecosystem in which we live.



'Ozone-depletion' potential: depletion of the ozone layer in the atmosphere caused by the emission of chemical foaming and cleaning agents allows the passage of greater levels of UV from the sun, causing skin cancer and reducing crop yields.




'Photochemical-oxidation' potential: where the photochemical reaction of sunlight with primary air pollutants such as volatile organic compounds and nitrogen oxides leads to chemical smogs that affect human health, food crops and the ecosystem in general.

COMPARISON BASED ON IDENTICAL FUNCTIONAL UNITS

For the purposes of a direct fair comparison between alternative materials the following identical functional unit was used in the LCA study for plumbing hot and cold solid wall systems:

- The pressure supply and transport of hot and cold drinking water from the entrance of an apartment of 100 m² to the tap
- A 50 year service life has been assumed which aligns with the normal lifetime expectancy of a building.

COMPARISON OF PEX TO COPPER FOR THE 6 ENVIRONMENTAL IMPACT CRITERIA



ENVIRONMENTAL PROFILE OF THE PEX PIPE SYSTEM FOR HOT AND COLD WATER IN THE BUILDING FROM CRADLE-TO-GRAVE PER FUNCTIONAL UNIT

